

## HumiSeal<sup>®</sup> 1C49HVF Silicone Encapsulant Technical Data Sheet

HumiSeal<sup>®</sup> 1C49HVF is a moisture curing, high build, VOC-free and solvent-free silicone encapsulant which provides excellent moisture and environmental protection for printed circuit assemblies. The encapsulant demonstrates outstanding flexibility, fluoresces under UV light for ease of inspection and is repairable. HumiSeal<sup>®</sup> 1C49HVF may be cured at room or elevated temperatures. HumiSeal<sup>®</sup> 1C49HVF is recognized under UL File Number E105698 and is RoHS Directive 2011/65/EU compliant.

### Properties of HumiSeal<sup>®</sup> 1C49HVF

Density, per ASTM D1475	0.97 ± 0.03 g/cm <sup>3</sup>
Viscosity, per Fed-Std-141, Meth. 4287	27500 ± 7500 centipoise
VOC	0 grams/liter
Working Time, at RT	10 min
Tack free time, at RT	20 min
Recommended Curing Conditions	24 hrs @ RT or 20 min @ 76°C*
Time required to Reach Optimum Properties	7 days
Recommended Stripper	HumiSeal <sup>®</sup> Stripper 1091
Shelf Life at Room Temperature, DOM	12 months
Flammability, per UL94	V-0
Shore Hardness, A, cured 72 hrs at RT, per ASTM D2240	25
Volume Resistivity, per ASTM D257	4.34 x 10 <sup>18</sup> ohm-cm

\*Place an open pan of water in the oven during curing

### Application of HumiSeal<sup>®</sup> 1C49HVF

Conformal coatings can be successfully applied to substrates that have been cleaned prior to coating and also to substrates assembled with low residue, "no clean" materials. Users should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials, process conditions and cleanliness level. Please contact HumiSeal for additional information.

1C49HVF is designed for application without additional thinning. Solvents or other thinners should not be mixed with 1C49HVF.

#### Syringe Application

HumiSeal<sup>®</sup> 1C49HVF is designed to be applied by hand syringes or automated needle dispensing such as a PVA FC100 needle valve, Asymtek SC-300 in monofilament mode or other automated dispensing equipment.

#### Brushing

HumiSeal<sup>®</sup> 1C49HVF may be applied by brush. The actual uniformity of the finished coating will depend on component density and operator technique. Brushes may be cleaned promptly using solvent.

## HumiSeal® 1C49HVF Technical Data Sheet

### Storage

HumiSeal® 1C49HVF should be stored at 27°C or below in tightly closed containers away from direct sunlight. If coating is partially used, the container should be purged with dry nitrogen prior to resealing. Prior to use, allow the product to equilibrate for 24 hours at room temperature.

### Caution

Application of HumiSeal® encapsulant should be carried out in accordance with local and National Health and Safety regulations.

Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult SDS prior to use.

## Contact HumiSeal®

### HumiSeal North America

201 Zeta Drive  
Pittsburgh, PA 15238  
USA  
Tel: +1 412-828-1500  
Toll Free (US only): 866-828-5470  
[sales@humiseal.com](mailto:sales@humiseal.com)

### HumiSeal Technical Center

295 University Avenue  
Westwood, MA 02090  
USA  
Tel: +1 781-332-0734  
Fax: +1 781-332-0703  
[techsupport@humiseal.com](mailto:techsupport@humiseal.com)

### HumiSeal Europe

505 Eskdale Road, IQ Winnersh  
Berkshire RG41 5TU  
UK  
Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europesales@chasecorp.com](mailto:europesales@chasecorp.com)

### HumiSeal India

J-154, M.I.D.C Bhosari  
Pune 411 026  
Maharashtra  
India  
Tel: +91 20 66308098  
[indiatechsupport@chasecorp.com](mailto:indiatechsupport@chasecorp.com)

### HumiSeal S.A.R.L

4/6 Avenue Eiffel  
78420 Carrieres-Sur-Seine  
France  
Tel: +33 (0) 1 30 09 86 86  
Fax: +33 (0) 1 30 09 86 87  
[humiseal.sarl@chasecorp.com](mailto:humiseal.sarl@chasecorp.com)

### HumiSeal Asian Support

Tel: 852-9451-6434  
Fax: 852-2413-6289  
[asiatechsupport@humiseal.com](mailto:asiatechsupport@humiseal.com)

### HumiSeal Europe Support

Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europetechsupport@chasecorp.com](mailto:europetechsupport@chasecorp.com)

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.