

HumiSeal® Vivid Cure™ UV9118T Black

Technical Data Sheet

SIDE SEAL

The Vivid Cure™ UV9118T Black is a thixotropic, fast curing urethane acrylate that bonds well to most glass and plastics.

APPLICATIONS

- Touch Screen Display
- Structural Support
- Damming Material
- Supports Bond Line Thickness

FEATURES

- Thixotropic
- Non-Yellowing, Clear
- Moisture Resistant
- UVA Curable

SUBSTRATES

- Plastics
- Glass
- Metals

Typical Properties of Uncured HumiSeal® Vivid Cure™ UV9118T*

Chemical Class	UV Acrylate
Appearance	Black
Viscosity @ 25°C, Spindle 7 @ 5 RPM, cps	200,000 to 500,000
Viscosity @ 25°C, Spindle 7 @ 50 RPM, cps	40,000 to 80,000
Specific Gravity	0.91
Cleanup Solvent	Isopropyl alcohol

Typical Properties of Cured Material

Glass Transition Temperature (Tg), °C	-45 to -50
Operating Temperature Range, °C	-50 to 125

*All properties given are typical values and are not intended for use in preparing specifications.

UV Curing Guidelines

HumiSeal Vivid Cure™ UV9118T Black adhesive has been formulated to allow flexibility in the curing process. HumiSeal Vivid Cure™ UV9118T Black can be cured using full spectrum mercury vapor light systems as well as 365nm and 395nm LED systems. The table below details minimum dosage values required to properly crosslink HumiSeal Vivid Cure™ UV9118T Black.

Note: Adhesive thickness range of 700 – 750 microns was used during the development of the minimum required dosage values recommended below. If a different adhesive thickness is used, process adjustments may be required.

Vivid Cure™ UV9118T Recommended Minimum Dose (J/cm ²)**	
Requirements	
Wavelength (nm)	UVA
365nm	1.7
395nm	1.9
Full Spectrum Mercury Vapor	2.6

Values measured with an EIT Powerpuck II

** These values are for guidelines only and not meant to be used as a specification

It is recommended that you contact HumiSeal technical support to discuss your application and review the required recommended minimum cure requirements.

Storage & Handling

Humiseal Vivid Cure™ UV9118T Black should be stored between 8°C - 28°C in tightly closed, light-blocking containers, away from direct sunlight. Keep from freezing. Allow material to equilibrate to process area temperature for 24 hours before use. Please refer to product labeling for shelf-life information. While the material can be heated to facilitate degassing prior to use, this operation should be conducted only on the amount of adhesive to be immediately used. Multiple heating cycles of the bulk container or elevated temperature storage of Humiseal Vivid Cure™ UV9118T Black should be avoided.

Consult SDS for full safety information.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.