

HumiSeal[®] 2C52 Thixotropic Silicone Gel

Technical Data Sheet

HumiSeal[®] 2C52 is a two-part silicone that cures rapidly at room temperature after mixing. It is designed for applications requiring a soft, high surface tack sealant with limited flowability after dispensing. HumiSeal[®] 2C52 adheres and seals most surfaces but can be easily removed and repaired after curing.

APPLICATIONS	FEATURES	SUBSTRATES
Wire Receptacles	RoHS & REACH Compliant	Plastics
Electronic Assemblies	Soft & Flexible	Metal
Power Supplies	Fast Setting	Circuit Board
Lighting Fixtures	Room Temperature Cure	Wire & Cable
	Water Resistant	Ceramic

Properties of HumiSeal[®] 2C52

Chemical Class	Silicone
Mixed Specific Gravity at 25°C	0.96-1.02
Viscosity, Spindle #6 at 20 rpm (Part A)	15,000 – 20,000 cps
Viscosity, Spindle #6 at 20 rpm (Part B)	10,000 – 20,000 cps
Mix Ratio (A:B)	1:1
Appearance	Clear-haze
Shelf Life @ 20 °C ± 10°C	6 Months
Pot Life at 25°C	10 minutes
Set Time at 25°C	15-25 minutes
Curing Conditions (5-gram mass)	1 hour at 25°C
	2 min. at 125°C
Hardness, TA-XT Texture Analyzer (g)	45-70
Cleanup Solvent	Isopropyl alcohol

Storage

HumiSeal[®] 2C52 should be stored between 10°C and 30°C in tightly closed containers away from heat.

Caution

Application of HumiSeal[®] 2C52 should be carried out in accordance with local and national health and safety regulations. Use only in well-ventilated areas to avoid inhalation of vapors. Avoid contact with skin and eyes.

Consult SDS prior to use.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal India

J-154, M.I.D.C Bhosari
Pune 411 026
Maharashtra
India
Tel: +91 20 66308098
indiatechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.