

HumiSeal[®] 1B31HS Acrylic Conformal Coating

Technical Data Sheet

HumiSeal[®] 1B31HS is a high viscosity and high solid content version of HumiSeal[®] 1B31. HumiSeal[®] 1B31HS is an acrylic coating demonstrates excellent flexibility, fluoresces under UV light for ease of inspection and is easily repaired. HumiSeal[®] 1B31HS coating is RoHS Directive 2002/95/EC compliant.

Properties of HumiSeal[®] 1B31HS

Density, per ASTM D1475	0.95 ± 0.02 g/cm ³
Solids Content, % by weight per Fed-Std-141, Meth. 4044	54.5 ± 1.0 %
Viscosity, per Fed-Std-141, Meth. 4287	6000 +/- 1500 cps
VOC	423 grams/liter
Drying Time to Handle per Fed-Std-141, Meth. 4061	10 minutes
Recommended Curing Conditions	24 hrs @ RT or 30 min @ 76°C
Time Required to Reach Optimum Properties	7 days
Recommended Stripper	HumiSeal [®] Stripper 1080
Shelf Life at Room Temperature, DOM	24 months

Application of HumiSeal[®] 1B31HS

Cleanliness of the substrate is extremely important to the successful application of a conformal coating. Surfaces should be free of moisture, dirt, wax, grease and all other contaminants. Otherwise, ionic or organic residues on the substrate could be trapped under the coating and cause problems with adhesion or electrical properties. The highest long term reliability for a coated printed circuit assembly will be when the conformal coating is applied over a clean, dry substrate. The application of conformal coatings over no clean flux is a common practice. The user should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials and process conditions.

Brushing

HumiSeal[®] 1B31HS may be brushed with an optional, but recommended, small addition of HumiSeal[®] Thinner 503. Uniformity of the film depends on component density and operator's technique.

Storage

HumiSeal[®] 1B31HS should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal[®] products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

Caution

Application of HumiSeal[®] Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal[®] Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

HumiSeal[®] 1B31HS Technical Data Sheet

Contact HumiSeal[®]

HumiSeal North America
201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center
295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe
505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L
4/6 Avenue Eiffel
78420 Carrières-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support
Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.