

Axis M-2

Technical Data Sheet

Axis M-2 is a medium viscosity epoxy resin system designed for medical and general adhesive and laminating applications in accordance with Title 21. U.S. Code of Federal Regulations, Food and Drug Administration (FDA) Chapter 1, Sub Part B, Sections 175, 105 and 175,300. This two-part epoxy is easily mixed, cures at room temperature and provides high strength bonds to a wide variety of substrates. Once cured, it is resistant to a wide range of chemicals, provides low permeability to gases and vapors, and is an excellent electrical insulator.

| APPLICATIONS | FEATURES | SUBSTRATES |
|-----------------------------|---------------------------------|-----------------------------|
| Industrial Adhesive | Biocompatible per ISO 10993-5 - | Various Plastics and Metals |
| | Pending | |
| Medical and food grade | Long work life | |
| instrument/packaging repair | | |
| Laminating | Room Temperature Cure | |
| | Impact and Peel Resistant | |
| | Thermal Shock Resistant | |

Typical Properties of Uncured Material*

| Chemical Class | Epoxy : Amine |
|---|-------------------|
| Color (Part A / Part B) | Clear : Amber |
| Viscosity, Part A @25°C, Spn7 @20RPM, cps | 11,000 – 15,000 |
| Viscosity, Part B @25°C, Spn7 @20RPM, cps | 12,000 – 18,000 |
| Specific Gravity Part A | 1.16 |
| Specific Gravity Part B | 0.98 |
| Mix Ratio, PBV (A:B) | 1:1 |
| Cleanup Solvent | Isopropyl alcohol |

Cure Guidelines*

| Work Life of 100 grams @ RT, minutes | 120 |
|--------------------------------------|-----|
| Gel Time of 100 grams @ RT, minutes | 180 |
| Cure Time @ RT, hours | 24 |
| Cure Time at 85°C, time | 2 |

Typical Properties of Cured Material*

| Durometer, Shore D | 78 |
|------------------------------------|------------|
| Elongation, % | <10% |
| Tensile Strength, MPa, [psi] | 38 [5,600] |
| Lap Shear Strength, Al / Al, psi | 750 |
| Lap Shear Strength, PCB / PCB, psi | 130 |

^{*}All properties given are typical values and are not intended for use in preparing specifications.

Storage

Keep stored between 8°C and 28°C in tightly sealed containers away from direct sunlight. Keep from freezing. Please refer to product labeling for shelf life information. Consult SDS for safe handling recommendations.



RESIN DESIGNS MAKES NO EXPRESSED OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT. APPLICATION OF THIS MATERIAL SHOULD COMPLY WITH LOCAL AND NATIONAL HEALTH AND SAFETY REGULATIONS.

Resin Designs 11 State Street, Woburn, MA 01801

www.resindesigns.com

781-935-3133