

ThermoSink 35-7

Technical Data Sheet

ThermoSink 35-7 is a two-component, thermally conductive silicone elastomer that cures rapidly at room temperature. ThermoSink 35-7 is designed for electrical potting and/or thermal interface applications where high-performance heat transfer and thermal management is required.

APPLICATIONS	FEATURES	SUBSTRATES
<ul style="list-style-type: none"> Automotive Electronic Assembly Power Supplies 	<ul style="list-style-type: none"> Thermally Conductive Water Resistant Fast set, Room-temperature Cure RoHS Compliant (Pending) 	<ul style="list-style-type: none"> Engineered Plastics Ceramics Plastics Metals

Typical Properties of Uncured Material*

Chemical Class	2K Silicone
Color (Part A / Part B)	Grey / White
Viscosity, Part A @25°C, @10RPM, cps	8,000 - 15,000
Viscosity, Part B @25°C, @10RPM, cps	4,000 - 9,000
Viscosity, Mixed @25°C, @10RPM, cps	6,000 - 10,000
Mixed Specific Gravity	2.7
Mix Ratio, PBW (A:B)	50:50
Cleanup Solvent	Isopropyl alcohol
Standard Operating Temperature Range, °C	- 40 to 200

Cure Guidelines*

Set Time @ 25°C, minutes	90 to 120
Cure Time @ 25°C, hours	5
Cure Time @ 100°C, minutes	45

Typical Properties of Cured Material*

Durometer, Shore A	20 - 30
Young's Modulus (At room temperature), MPa	12
Glass Transition Temperature, °C	-47
CTE, ppm, Above Tg	~200
Dielectric Constant, @ 1 MHz, ASTM D150	8.18
Dielectric Strength, Volt/mil, ASTM D149	247
Volumetric Resistivity, Ω*cm, ASTM D257	1 x 10 ¹⁴
Dissipation Factor, @ 1 MHz, ASTM D150	0.029
Thermal Conductivity, W/m °K	>2.5
Flammability, UL94**	V0
Outgassing, ASTM E595-15	Meets Requirements

*All properties given are typical values and are not intended for use in preparing specifications.

** Flammability tested in-house with 3 mm thick sample using identical conditions as UL94 flame chamber

Storage

Both Part A and Part B need to be thoroughly remixed individually prior to use. Keep stored between 8°C and 28°C in tightly closed, light-blocking containers away from direct sunlight. Keep from freezing Please refer to product labeling for shelf-life information. Consult SDS for safe handling recommendations.



RESIN DESIGNS MAKES NO EXPRESSED OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT. APPLICATION OF THIS MATERIAL SHOULD COMPLY WITH LOCAL AND NATIONAL HEALTH AND SAFETY REGULATIONS.

www.resindesigns.com