



HM 002

Technical Data

Typical Properties:

Application Temperature	> 250° F
Viscosity (250° F)	18,000 cps
Viscosity (275° F)	11,150 cps
Viscosity (300° F)	9,000 cps
Softening Point	179° F
Absorption Capacity (g/g deionized water)	> 130
Specific Gravity	1.25

Chemistry:	Hot melt adhesive containing superabsorbent polymer
Appearance:	Solid
Storage:	One year in unopened containers between 60° F and 120° F
Packaging:	Bricks

Technical information is based on current knowledge and is offered to inform and advise subject to your further investigation and verification. Modifications may be made in the interest of technical improvement. No warranties are expressed or implied as the use of the product is beyond our control.

Stewart Superabsorbents LLC
1954 Main Avenue SE
Hickory, NC 28602 USA
T: +1 828 855 9316 F: +1 828 855 9319
www.stewartsuperabsorbents.com
A member of The Stewart Group of companies

Richard Ellis
Cable Materials Inc.
T: +1 678 691 6398
M: +1 678 848 4805
E: rellisga@cablematerialsinc.com